



RECEIVED

OCT 23 2002

15 1700

Attorney Docket no: SEL 233

17682

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Yamazaki et al.

Serial No.: 09/747,731

Filed: December 22, 2000

For: Method Of Manufacturing A Display
Device

Examiner: W. Fletcher III

Art Unit: 1762

I hereby certify that this correspondence is being
deposited with the United States Postal Service as
first class mail in an envelope addressed to:
the Assistant Commissioner for Patents, Washington,
D.C. 20231 on 10-15-02
(Date of Deposit)

Rachelle Hammerger
Name of applicant, assignee, or Registered Rep.
[Signature] 10-15-02
Signature Date

Commissioner for Patents
Washington D.C. 20231

TRANSMITTAL OF VERIFIED TRANSLATION OF PRIORITY DOCUMENT

In Amendment A filed on September 30, 2002 in response to the Office Action of May 28, 2002, Applicants distinguished over the rejection of Claim 20 under 35 USC §103 as being unpatentable over Mizutani et al. in view of Takacs et al. and further in view of Grothe et al. and still further in view Namiki et al. by stating as follows:

“Takacs has a filing date of December 30, 1999 and an issue date of June 12, 2001. The present application was filed on December 22, 2000 but claims priority under 35 USC §119 to Japanese application serial no. 11-371349 which was filed on December 27, 1999. A certified copy of this priority document was filed on December 22, 2000 with the present application. As this priority date is prior to the filing date of Takacs, Takacs is not prior art to the present application, and the rejection based thereon should be withdrawn.”


At that time, Applicants also stated that a verified translation of the priority document was being prepared and would be submitted in the near future. Applicants have now prepared such a

verified translation and are submitting it herewith. Accordingly, it is requested that this rejection of Claim 20 now be withdrawn.

If any fee should be due for this submission, please charge our deposit account 50/1039.

Favorable reconsideration is earnestly solicited.

Respectfully submitted,


Mark J. Murphy
Registration No. 34,225

COOK, ALEX, McFARRON, MANZO,
CUMMINGS & MEHLER, Ltd.
200 West Adams Street, Suite 2850
Chicago, Illinois 60606
(312) 236-8500



RECEIVED

OCT 23 2002

TC 1700

Docket No.: SEL 233

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of:)
Shunpei YAMAZAKI et al)
Application No.: 09/747,731) Group Art Unit: 1762
Filed: December 22, 2000) Examiner: W. FLETCHER III
For: FILM FORMATION APPARATUS
AND METHOD FOR FORMING A FILM)

VERIFICATION OF TRANSLATION

Honorable Commissioner of Patents and Trademarks
Washington, D.C. 20231

Sir:

I, Noriko Inage, 116-2, Kamiohi, Ohi-machi, Ashigarakami-gun, Kanagawa-ken 258-0016 Japan, a translator, herewith declare:

that I am well acquainted with both the Japanese and English Languages;

that I am the translator of the attached translation of the Japanese Patent Application No. 11-371349 filed on December 27, 1999; and

that to the best of my knowledge and belief the followings is a true and correct translation of the Japanese Patent Application No. 11-371349 filed on December 27, 1999.

I further declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that theses statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Date: this 7th day of October 2002

Name: Noriko Inage

[Name of Document] Patent Application
[Reference Number] P004528-12
[Filing Date] December 27, 1999
[Attention] Commissioner, Patent Office
[International Patent Classification] H01L 21/00
[Inventor]
 [Address] 398, Hase, Atsugi-shi, Kanagawa-ken
 c/o Semiconductor Energy Laboratory Co., Ltd.
 [Name] Shunpei YAMAZAKI
[Inventor]
 [Address] 398, Hase, Atsugi-shi, Kanagawa-ken
 c/o Semiconductor Energy Laboratory Co., Ltd.
 [Name] Takeshi FUKUNAGA
[Applicant]
 [Identification Number] 000153878
 [Name] Semiconductor Energy Laboratory Co., Ltd.
 [Representative] Shunpei YAMAZAKI
[Indication of Handlings]
 [Number of Prepayment Note] 002543
 [Payment Amount] 21000
[List of Attachment]
 [Attachment] Specification 1
 [Attachment] Drawing 1
 [Attachment] Abstract 1
[Proof] required

[Name of Document] Specification

[Title of the Invention]

FILM FORMATION APPARATUS AND METHOD FOR FORMING A FILM

[Scope of Claim]

[Claim 1]

A film formation apparatus comprising:

an evaporation source having a longitudinal direction; and
a mechanism for moving the evaporation source in a direction perpendicular to the longitudinal direction of the evaporation source.

[Claim 2]

A film formation apparatus comprising:

an evaporation source having a longitudinal direction;
a mechanism for moving said evaporation source in the direction perpendicular to the longitudinal direction of the evaporation source; and
an electromagnet formed over top of the mechanism.

[Claim 3]

A film formation apparatus comprising:

a load chamber;
a conveyor chamber connected to the load chamber; and
a evaporation chamber connected to the conveyor chamber,
wherein said evaporation chamber includes a evaporation source having longitudinal direction and a mechanism for moving the evaporation source in a direction perpendicular to the longitudinal direction of the evaporation source.

[Claim 4]

A film formation apparatus comprising:

a load chamber;

a conveyor chamber connected to the load chamber; and
a evaporation chamber connected to the conveyor chamber,
wherein said evaporation chamber includes a evaporation source
having longitudinal direction, a mechanism for moving the evaporation
source in a direction perpendicular to the longitudinal direction of the
evaporation source, and an electromagnet formed over top of the mechanism.

[Claim 5]

A film formation apparatus comprising:

a load chamber;
an unload chamber; and
an evaporation chamber,

wherein said load chamber, said unload chamber and said evaporation
chamber are connected in series, and

wherein the evaporation chamber includes an evaporation source
having a longitudinal direction and a mechanism for moving the evaporation
source in a direction perpendicular to the longitudinal direction of the
evaporation source.

[Claim 6]

A film formation apparatus comprising:

a load chamber;
an unload chamber; and
an evaporation chamber,

wherein said load chamber, said unload chamber and said evaporation
chamber are connected in series, and

wherein the evaporation chamber includes an evaporation source
having a longitudinal direction, a mechanism for moving the evaporation
source in a direction perpendicular to the longitudinal direction of the
evaporation source, and an electromagnet formed over top of the mechanism.

[Claim 7]

A film formation apparatus as claimed in any one of Claims 1 to 6, wherein the evaporation source is provided with an evaporation cell having a longitudinal direction.

[Claim 8]

A film formation apparatus claimed in any one of Claim 1 to 6, wherein the evaporation source is provided with a plurality of evaporation cells.

[Claim 9]

A method of forming a thin film over a substrate while moving an evaporation source, having a longitudinal direction, in a direction perpendicular to the longitudinal direction of the evaporation source.

[Claim 10]

A method of forming a thin film over a substrate while moving an evaporation source, having a longitudinal direction, in a direction perpendicular to the longitudinal direction of the evaporation source, wherein the substrate and a shadow mask composed of a metal are in a state of contact in accordance with an electromagnet.

[Detailed Description of the Invention]

[0001]

[Technical Field to which the Invention Pertains]

The present invention relates to an apparatus or a method for forming a film used in manufacturing an EL (electroluminescence) element having a structure composed of an anode, a cathode, and sandwiching between the anode and the cathode a light emitting material, in particular a self-luminous organic material (hereafter referred to as an organic EL material), from which EL (Electro Luminescence) is obtained.

[0002]

[Prior Art]

In recent years, development is proceeding on display devices using an EL element as a self-luminous element that emits light through EL phenomenon of an organic EL material (hereafter referred to as EL display devices). Since the EL display devices are a self-luminous type, the EL display devices do not need backlight unlike liquid crystal display devices. Further, the EL display devices have also wide viewing angle, which makes them prospective display portions for portable equipments used outdoors.

[0003]

There are two types of EL display devices, a passive type (a simple matrix type), and an active type (an active matrix type), and development of both is being enthusiastically performed. In particular, active matrix type EL display devices are in the spotlight at present. Furthermore, organic materials and inorganic materials exist for an EL material which becomes a light emitting layer of an EL element, and in addition organic materials are divided into low molecular weight (monomer) organic EL materials and high molecular weight (polymer) organic EL materials. Both are being vigorously researched, but a film of a low molecular weight organic EL material is mainly formed by evaporation, while a film of a high polymer organic EL material is mainly formed by application.

[0004]

In order to manufacture an EL display device of color display, it is necessary to form films of EL materials which emit different colors, for each pixel. However, in general EL materials are weak with respect to water and oxygen, and patterning by photolithography cannot be performed. It is therefore necessary to form the films at the same time as patterning.

[0005]

The most general method is a method for forming a mask (hereafter referred to as a shadow mask), made from a metallic plate or a glass plate

and having an opening portion formed in it, between the substrate onto which a film is formed and an evaporation source. In this case, the vaporized EL material from the evaporation source passes through only the opening portion to thereby form the film selectively, and therefore it is possible to form an EL layer in which film formation and patterning are performed simultaneously.

[0006]

With a conventional evaporation apparatus, the EL material which flies off in a radial shape from one evaporation source accumulates on a substrate, forming a thin film, and therefore, considering the distance that the EL material covers, a way of substrate positioning was devised. For example, a method of fixing a substrate to a circular cone shaped substrate holder, making the distances from the evaporation source to the substrate all equal, is performed.

[0007]

However, when employing a multi-beveling process in which a plurality of panels are manufactured on a large size substrate, the substrate holder becomes extremely large if the above stated process is performed, and this leads to the main body of the film formation apparatus becoming large. Further, the substrate is planar when performing by single wafer processing as well, and therefore the distances from the evaporation source differs within the surface of the substrate, and a problem remains in that it is difficult to deposit at a uniform film thickness.

[0008]

In addition, if the distance between the evaporation source and the shadow mask is not made longer when using a large size substrate, the vaporized EL material does not sufficiently spread, and it becomes difficult to form a uniform thin film over the entire substrate surface.

Maintaining this distance also encourages making the apparatus large size.

[0009]

[Problem to be Solved by the Invention]

The present invention is made in view of the above stated problems, and an object of the present invention is to provide a film formation apparatus capable of forming a thin film having a highly uniform film thickness distribution at high throughput. Further, an object of the present invention is to provide a method of forming a film using the film formation apparatus of the present invention.

[0010]

[Means for Solving the Problem]

An evaporation source in which an evaporation cell (a portion in which a thin film material for evaporation is placed) or a plurality of the evaporation cells having a longitudinal direction, are formed is used in the present invention. By moving the evaporation source in a direction perpendicular to the longitudinal direction of the evaporation source, a thin film is formed. Note that, "having a longitudinal direction" indicates a long and thin rectangular shape, a long and thin elliptical shape, or a linear shape.

[0011]

The positional relationship between the evaporation source and the substrate of the present invention is shown in Figs. 1A to 1C. Fig. 1A is a top view, Fig. 1B is a cross sectional diagram of Fig. 1A cut along a line A-A', and Fig. 1C is a cross sectional diagram of Fig. 1A cut along a line B-B'. Note that, common symbols are used in Figs. 1A to 1C.

[0012]

As shown in Fig. 1A, a shadow mask 102 is placed below a substrate 101, and in addition, a rectangular shaped evaporation source 104, in which

a plurality of evaporation cells 103 are lined up on a straight line, is placed below the shadow mask 102. Note that, throughout this specification, the term substrate includes a substrate and thin films formed on that substrate. Further, the term substrate surface indicates the substrate surface on which the thin films are formed.

[0013]

The length of the longitudinal direction of the evaporation source 104 is longer than the length of one side of the substrate 101, and a mechanism for moving the evaporation source 104 in a direction shown by an arrow (a direction perpendicular to the longitudinal direction of the evaporation source 104) is prepared. By then moving the evaporation source 104, a thin film can be formed over the entire surface of the substrate. Note that, when the length of the longitudinal direction is shorter than that of one side of the substrate, the thin film may be formed by repeating a plurality of scans. Furthermore, a lamination of the same thin film may be formed by repeatedly moving the evaporation source 104.

[0014]

The thin film material vaporized by each of the evaporation cells 103 is scattered in the upward direction, passes through opening portions (not shown in the figures) formed in the shadow mask 102, and accumulates on the substrate 101. The thin film is thus selectively deposited on the substrate 101. A region in which the thin film material scattered from one evaporation cell 103 forms a film overlaps with a region in which the thin film material scattered from an adjoining evaporation cell 103 forms a film. By mutually overlapping the regions in which the film is deposited, the film is formed in a rectangular shape region.

[0015]

The uniformity in film thickness of a thin film can thus be greatly

improved with the present invention by using the evaporation source having a plurality of evaporation cells lined up, and by irradiating from a line instead of conventional irradiation from a point. In addition, by moving the rectangular shape evaporation source below the substrate surface, film formation can be performed at high throughput.

[0016]

Additionally, it is not necessary to make the distance between the evaporation source 104 and the shadow mask 102 longer with the present invention, and evaporation can be performed in a state of extreme closeness. This is because a plurality of evaporation cells are formed in alignment, and even if the scattering distance of the thin film material is short, film formation can be performed simultaneously from the central portion to the edge portion of the substrate. This effect is greater the higher the density at which the evaporation cells 103 are lined up.

[0017]

The distance from the evaporation source 104 to the shadow mask 102 is not particularly limited because it differs depending upon the density at which the evaporation cells 103 are formed. However, if it is too close, then it becomes difficult to form a uniform film from the center portion to the edge portion, and if it is too far, there will be no change from conventional evaporation by irradiating from a point. Therefore, if the gap between evaporation cells 103 is taken as "a", it is preferable to make the distance between the evaporation source 104 and the shadow mask 102 from 2a to 100a (more preferably from 5a to 50a).

[0018]

With the film formation apparatus of the present invention structured as above, uniformity of the distribution of film thickness of a thin film in a rectangular shape, elliptical shape, or a linear shape

region is maintained by using the evaporation source, and by moving the evaporation source on top of that region, it becomes possible to form a thin film having high uniformity over the entire surface of the substrate. Further, this is not evaporation from a point, and therefore the distance between the evaporation source and the substrate can be made shorter, and the uniformity of film thickness can be further increased.

[0019]

Furthermore, it is effective to add means for generating a plasma within a chamber in the film formation apparatus of the present invention. By performing a plasma process in accordance with oxygen gas or a plasma process in accordance with a gas containing fluorine, thin films deposited on the chamber walls are removed, and cleaning of the inside of the chamber can be performed. Parallel-plate electrodes may be formed within the chamber, and a plasma may be generated between the plates as the means for generating the plasma.

[0020]

[Embodiment Modes of the Invention]

A structure of an evaporation chamber prepared in a film formation apparatus of the present invention is shown in Figs. 2A and 2B. Fig. 2A is a top view of the evaporation chamber, and Fig. 2B is a cross sectional diagram. Note that common symbols are used for common portions. Further, an example of forming an EL (electroluminescence) film as a thin film is shown in the embodiment mode.

[0021]

In Fig. 2A, reference numeral 201 denotes a chamber, and reference numeral 202 denotes a substrate conveyor opening, from which a substrate is conveyed to the inside portion of the chamber 201. A conveyed substrate 203 is set in a substrate holder 204, and is conveyed in to a film formation

portion 206 by a conveyor rail 205, as shown by an arrow 205.

[0022]

When the substrate 203 is conveyed to a film formation portion 206, a shadow mask 208 fixed to a mask holder 207 approaches the substrate 203. Note that, a metallic plate is used as the material of the shadow mask 208 in this embodiment mode (See Fig. 2B). Further, open portions 209 are formed having a rectangular shape, elliptical shape, or linear shape in the shadow mask 208 in this embodiment mode. The shape of the opening portions is not limited thereto, of course, and a matrix shape or a net shape may also be formed.

[0023]

At this point in the embodiment mode, this is a structure in which an electromagnet 210 approaches the substrate 203, as shown in Fig. 2B. When a magnetic field is formed by the electromagnet 210, the shadow mask 208 is drawn to the substrate 203, and is maintained at a predetermined gap. This gap is secured by a plurality of projections 301 formed in the shadow mask 208, as shown in Fig. 3.

[0024]

This type of structure is particularly effective when the substrate 203 is a large size substrate exceeding 300 mm. If the substrate 203 is large size, then deflection is generated by the weight of the substrate itself. However, the substrate 203 can also be pulled toward the electromagnet 210 and the flexure can be canceled provided that the shadow mask 208 is drawn toward the substrate 203 side by the electromagnet 210. Note that, as shown in Fig. 4, it is preferable to form projections 401 in the electromagnet 210, and to maintain a gap between the substrate 203 and the electromagnet 210.

[0025]

When the gap between the substrate 203 and the shadow mask 208 is secured, an evaporation source 212, on which evaporation cells 211 having a longitudinal direction are formed, is then moved in the direction of the arrow 213. An EL material formed in the inside portion of the evaporation cells is vaporized by being heated while being moved, and is scattered within the chamber of the film formation portion 206. Note that the distance between the evaporation source 212 and the substrate 203 can be made extremely short for the case of the present invention, and therefore adhesion of the EL material to a drive portion (a portion for driving the evaporation source, the substrate holder, or the mask holder) within the chamber can be minimized.

[0026]

The evaporation source 212 is scanned from one end of the substrate 203 to the other end. As shown in Fig. 2A, the length of the longitudinal direction of the evaporation source 212 is sufficiently long in the embodiment mode, and therefore it can be moved over the entire surface of the substrate 203 by scanning once.

[0027]

After a film is formed from a red, green, or blue color EL material (red here) as above, the magnetic field of the electromagnet 210 is switched off, the mask holder 207 is dropped down, and the distance between the shadow mask 208 and the substrate 203 increases. The substrate holder 204 is then shifted over by one pixel portion, the mask holder 207 is raised again, and the shadow mask 208 and the substrate 203 are made to come closer. In addition, a magnetic field is formed by the electromagnet 210, and deflection of the shadow mask 208 and the substrate 203 is eliminated. The evaporation cell is changed next, and film formation of a red, green, or blue EL material (green here) is performed.

[0028]

Note that, a structure in which the substrate holder 204 is shifted by one pixel portion is shown here, but the mask holder 204 may also be shifted by one pixel portion.

[0029]

After all film formation of red, green, and blue EL materials by this type of repetition, the substrate 203 is lastly conveyed to the substrate conveyor opening 202, and is removed from the chamber 201 by a robot arm (not shown in the figures). Film formation of the EL films using the present invention is thus completed.

[0030]

[Embodiments of the Invention]

[Embodiment 1]

An explanation of a film formation apparatus of the present invention is explained using Fig. 5. In Fig. 5, reference numeral 501 denotes a conveyor chamber. A conveyor mechanism 502 is prepared in the conveyor chamber 501, and conveyance of a substrate 503 is performed. The conveyor chamber 501 has a reduced pressure atmosphere, and is connected to each processing chamber by a gate. Delivery of the substrate to each processing chamber is performed by the conveyor mechanism 502 when the gates are open. Further, it is possible to use an evacuation pump such as an oil-sealed rotary pump, a mechanical booster pump, a turbo-molecular pump, and a cryo-pump in lowering the pressure of the conveyor chamber 501, but a cryo-pump, which is effective in removing moisture, is preferable.

[0031]

An explanation regarding each processing chamber is made below. Note that the conveyor chamber 501 has a reduced pressure atmosphere, and therefore an evacuation pump (not shown in the figure) is prepared in each

processing chamber directly connected to the conveyor chamber 501. The above stated oil-sealed rotary pump, mechanical booster pump, turbo-molecular pump, and cryo-pump are used as the evacuation pump.

[0032]

First, reference numeral 504 denotes a load chamber for performing substrate setting, and it is also an unload chamber. The load chamber 504 is connected to the conveyor chamber 501 by a gate 500a, and a carrier (not shown in the figure) on which the substrate 503 is set is arranged here. Note that the load chamber 504 may also be separated into a substrate loading chamber and a substrate unloading chamber. Further, the above evacuation pump and a purge line for introducing high purity nitrogen gas or noble gas are prepared for the load chamber 504.

[0033]

Note that a substrate on which process through the formation of a transparent conducting film, which becomes an anode of an EL element has been conducted, is used as the substrate 503 in Embodiment 1. The substrate 503 is set in the carrier with the surface on which the films are formed facing downward. This is in order to make a face-down method (also referred to as a deposition-up method) easier to perform when later performing film formation by evaporation. The face down method denotes a method in which film formation is performed with the substrate surface onto which a film is to be formed facing downward, and adhesion of dirt or the like can be suppressed by this method.

[0034]

Next, reference numeral 505 denotes a processing chamber (hereafter referred to as a preprocessing chamber) for processing a surface of an anode or a cathode of an EL element (in Embodiment 1, an anode), and the preprocessing chamber 505 is connected to the conveyor chamber 501 by a

gate 500b. The preprocessing chamber can be changed variously depending upon the manufacturing process of the EL element, and in Embodiment 1 heat treatment of the surface of the anode made from the transparent conducting film can be performed at between 100 and 120°C in oxygen while irradiating ultraviolet light. This type of pre-process is effective when processing the anode surface of the EL element.

[0035]

Next, reference numeral 506 denotes an evaporation chamber for film deposition of an organic EL material by evaporation, and is referred to as an evaporation chamber (A). The evaporation chamber (A) 506 is connected to the conveyor chamber 501 through a gate 500c. In Embodiment 1, an evaporation chamber having the structure shown in Figs. 2A and 2B is used as the evaporation chamber (A) 506.

[0036]

In a film formation portion 507 inside of the evaporation chamber (A) 506, first a hole injecting layer is deposited over the entire substrate surface, then a light emitting layer for emitting red color light is formed, next a light emitting layer for emitting green color light is formed, and lastly a light emitting layer for emitting blue color light is formed. Note that any known materials may be used as the hole injecting layer, the red color light emitting layer, the green color light emitting layer, and the blue color light emitting layer.

[0037]

The evaporation chamber (A) 506 has a structure which is capable of switching in correspondence with the type of organic material of the film formation evaporation source. Namely, a preparation chamber 508 for storing a plurality of types of evaporation sources is connected to the evaporation chamber (A) 506, and evaporation source switching is performed

by an internal conveyor mechanism. The evaporation source therefore changes when the organic EL material for film formation changes. Further, the same mask of shadow mask is moved by one pixel portion whenever the organic EL material for film formation is switched.

[0038]

Note that Figs. 2A and 2B may be referred to regarding film formation processes occurring within the evaporation chamber (A) 506.

[0039]

Next, reference numeral 509 denotes an evaporation chamber for film formation of a conducting film (a metallic film which becomes a cathode is used in Embodiment 1), which becomes an anode or a cathode of the EL element, by evaporation, and is referred to as an evaporation chamber (B). The evaporation chamber (B) 509 is connected to the conveyor chamber 501 through a gate 500d. An evaporation chamber having the structure shown in Figs. 2A and 2B is used as the evaporation chamber (B) 509 in Embodiment 1. In a film formation portion 510 within the evaporation chamber (B) 509, an Al-Li alloy film (an alloy film of aluminum and lithium) is deposited as the conducting film which becomes the EL element cathode.

[0040]

Note that it is also possible to co-evaporate an element belonging to group 1 or group 2 of the periodic table, and aluminum. Co-evaporation refers to evaporation in which cells are heated at the same time, and different materials are combined at the stage of film formation.

[0041]

Next, reference numeral 511 denotes a sealing chamber (also referred to as an enclosing chamber or a globe box), and is connected to the load chamber 504 through a gate 500e. A process for final hermetic sealing of the EL element is performed in the sealing chamber 511. This process is

one in which the formed EL element is protected from oxygen and moisture, and a means for mechanically sealing by a sealing material, or a means for sealing by a thermally hardened resin or an ultraviolet light hardened resin is used.

[0042]

Glass, ceramic, plastic, and metal can be used as the sealing material, but when light is irradiated onto the sealing material side, the material must have transparency. Further, when the sealing material and substrate on which the above EL element is formed are joined using a thermal hardened resin or an ultraviolet light hardened resin, the resin is hardened by heat treatment or by ultraviolet light irradiation processing, forming an airtight space. It is also effective to form a hygroscopic agent, typically barium oxide, within the airtight space.

[0043]

Further, it is also possible to fill the space between the sealing material and the substrate on which the EL element is formed by a thermal hardened resin or an ultraviolet light hardened resin. In this case, it is effective to add a hygroscopic agent, typically barium oxide, within the thermal hardened resin or the ultraviolet light hardened resin.

[0044]

A mechanism for irradiating ultraviolet light (hereafter referred to as an ultraviolet light irradiation mechanism) 512 is formed on an internal portion of the sealing chamber 511, and the film formation apparatus shown in Fig. 5 has a structure in which an ultraviolet light hardened resin is hardened by ultraviolet light emitted from the ultraviolet light irradiation mechanism 512. Further, it is possible to reduce the pressure of the inside portion of the sealing chamber 511 by attaching an evacuation pump. When mechanically performing the above

sealing processes by using robot operation, oxygen and moisture can be prevented from mixing in by performing the processes under reduced pressure. Furthermore, it is also possible to pressurize the inside portion of the sealing chamber 511. In this case pressurization is performed by a high purity nitrogen gas or noble gas while purging, and an incursion of a contaminant such as oxygen from the atmosphere is prevented.

[0045]

Next, a delivery chamber (a pass box) 513 is connected to the sealing chamber 511. A conveyor mechanism (B) 514 is formed in the delivery chamber 513, and the substrate on which the EL element has been completely sealed in the sealing chamber 511 is conveyed to the delivery chamber 513. It is possible to also make the delivery chamber 513 reduced pressure by attaching an evacuation pump. The delivery chamber 513 is equipment used so that the sealing chamber 511 is not directly exposed to the atmosphere, and the substrate is removed from here.

[0046]

As described above, it thus becomes possible to manufacture an EL display device having high reliability by using the film formation apparatus shown in Fig. 5 because processing can be finished up through the point, without exposure to the atmosphere, at which the EL element is completely sealed into an airtight space.

[0047]

[Embodiment 2]

A case of using a film formation apparatus of the present invention in a multi-chamber method (also referred to as a cluster tool method) is explained using Fig. 6. Reference numeral 601 denotes a conveyor chamber in Fig. 6. A conveyor mechanism (A) 602 is prepared in the conveyor chamber 601, and conveyance of a substrate 603 is performed. The conveyor chamber

601 has a reduced pressure atmosphere, and is connected to each processing chamber by a gate. Delivery of the substrate to each processing chamber is performed by the conveyor mechanism (A) 602 when the gates are open. Further, it is possible to use an evacuation pump such as an oil-sealed rotary pump, a mechanical booster pump, a turbo-molecular pump, and a cryo-pump in lowering the pressure of the conveyor chamber 601, but a cryo-pump, which is effective in removing moisture, is preferable.

[0048]

An explanation regarding each processing chamber is made below. Note that the conveyor chamber 601 has a reduced pressure atmosphere, and therefore an evacuation pump (not shown in the figure) is prepared in each processing chamber directly connected to the conveyor chamber 601. The above stated oil-sealed rotary pump, mechanical booster pump, turbo-molecular pump, and cryo-pump is used as the evacuation pump.

[0049]

First, reference numeral 604 denotes a load chamber for performing substrate setting, and it is also called a load-locking chamber. The load chamber 604 is connected to the conveyor chamber 601 by a gate 600a, and a carrier (not shown in the figure) on which the substrate 603 is set is arranged here. Note that the load chamber 604 may also be separated into a substrate loading chamber and a substrate unloading chamber. Further, the above evacuation pump and a purge line for introducing high purity nitrogen gas or noble gas are prepared for the load chamber 604.

[0050]

Next, reference numeral 605 denotes a preprocessing chamber for processing a surface of an anode or a cathode of an EL element (in Embodiment 2, an anode), and the preprocessing chamber 605 is connected to the conveyor chamber 601 by a gate 600b. The preprocessing chamber can be changed

variously depending upon the manufacturing process of the EL element, and in Embodiment 2 heat treatment of the surface of the anode made from the transparent conducting film can be performed at between 100 and 120°C in oxygen while irradiating ultraviolet light. This type of pre-process is effective when processing the anode surface of the EL element.

[0051]

Next, reference numeral 606 denotes an evaporation chamber for film deposition of an organic EL material by evaporation, and is referred to as an evaporation chamber (A). The evaporation chamber (A) 606 is connected to the conveyor chamber 601 through a gate 600c. In Embodiment 2 an evaporation chamber having the structure shown in Figs. 2A and 2B is used as the evaporation chamber (A) 606.

[0052]

In a film formation portion 607 inside of the evaporation chamber (A) 606, a hole injecting layer and a light emitting layer for emitting red color light is formed. Accordingly, an evaporation source and a shadow mask are provided with two types of each corresponding to the organic material to be the hole injecting layer and the red color light emitting layer, and are structured to be capable of switching. Note that known materials may be used as the hole injecting layer, and the red color light emitting layer.

[0053]

Next, reference numeral 608 denotes an evaporation chamber for film formation of an organic EL material by evaporation, and is referred to as an evaporation chamber (B). The evaporation chamber (B) 608 is connected to the conveyor chamber 601 through a gate 600d. In Embodiment 2, an evaporation chamber with the structure shown in Figs. 2A and 2B is used as the evaporation chamber (B) 608. A light emitting layer for emitting

green color light is deposited in a film formation portion 609 within the evaporation chamber (B) 608 in Embodiment 2. Note that a known material may be used as the light emitting layer for emitting green color light in Embodiment 2.

[0054]

Next, reference numeral 610 denotes an evaporation chamber for film formation of an organic EL material by evaporation, and is referred to as an evaporation chamber (C). The evaporation chamber (C) 610 is connected to the conveyor chamber 601 through a gate 600e. In Embodiment 2, an evaporation chamber with the structure shown in Figs. 2A and 2B is used as the evaporation chamber (C) 610. A light emitting layer for emitting blue color light is deposited in a film formation portion 611 within the evaporation chamber (C) 610 in Embodiment 2. Note that a known material may be used as the light emitting layer for emitting blue color light in Embodiment 2.

[0055]

Next, reference numeral 612 denotes an evaporation chamber for film formation of a conductive film, which becomes an anode or a cathode of the EL element, by evaporation (a metallic film which becomes a cathode is used in this embodiment), and is referred to as an evaporation chamber (D). The evaporation chamber (D) 612 is connected to the conveyor chamber 601 through a gate 600f. An evaporation chamber having the structure shown in Figs. 2A and 2B is used as the evaporation chamber (D) 612 in Embodiment 2. In a film formation portion 613 within the evaporation chamber (D) 612, an Al-Li alloy film (an alloy film of aluminum and lithium) is deposited as the conducting film which becomes a cathode of the EL element. Note that it is also possible to co-evaporate an element belonging to group 1 or group 2 of the periodic table, and aluminum.

[0056]

Next, reference numeral 614 denotes a sealing chamber, and is connected to the load chamber 604 through a gate 600g. For explanation of the sealing chamber 614 refer to Embodiment 1. Further, an ultraviolet light irradiation mechanism 615 is formed in the inside portion of the sealing chamber 614, similar to Embodiment 1. In addition, a delivery chamber 616 is connected to the sealing chamber 615. A conveyor mechanism (B) 617 is formed in the delivery chamber 616, and the substrate, on which the EL element has been completely sealed in the sealing chamber 614, is conveyed to the delivery chamber 616. Embodiment 1 may be referred to for an explanation of the delivery chamber 616.

[0057]

As mentioned above, it thus becomes possible to manufacture an EL display device having high reliability by using the film formation apparatus shown in Fig. 6 because processing can be finished up through the point, without exposure to the atmosphere, at which the EL element is completely sealed into an airtight space.

[0058]

[Embodiment 3]

A case of using a film formation apparatus of the present invention in an in-line method is explained using Fig. 7. Reference numeral 701 denotes a load chamber in Fig. 7, and conveyance of a substrate is performed here. An evacuation system 700a is prepared in the load chamber 701, and the evacuation system 700a has a structure containing a first valve 71, a turbo-molecular pump 72, a second valve 73, and a rotary pump (oil-sealed rotary pump) 74.

[0059]

The first valve 71 is a main valve, and there are cases when it also

combines a conductance valve, and there are also cases when a butterfly valve is used. The second valve 73 is a fore valve, and the second valve 73 is opened first, and the load chamber 701 is roughly reduced in pressure by the rotary pump 74. The first valve 71 is opened next, and the pressure is reduced by the turbo-molecular pump 72 until a high vacuum is reached. Note that it is possible to use a mechanical booster pump or a cryo-pump as a substitute for the turbo-molecular pump, but the cryo-pump is particularly effective in removing moisture.

[0060]

Next, reference numeral 702 denotes a preprocessing chamber for processing a surface of an anode or a cathode of an EL element (in Embodiment 3, an anode), and the preprocessing chamber 702 is prepared with an evacuation system 700b. Further, it is hermetically sealed off from the load chamber 701 by a gate not shown in the figure. The preprocessing chamber 702 can be changed variously depending upon the manufacturing process of the EL element, and in Embodiment 3 heat treatment of the surface of the anode made from the transparent conducting film can be performed at between 100 and 120°C in oxygen while irradiating ultraviolet light.

[0061]

Next, reference numeral 703 denotes an evaporation chamber for film deposition of an organic EL material by evaporation, and is referred to as an evaporation chamber (A). The evaporation chamber (A) 703 is included with an evacuation system 700c. Further, it is hermetically sealed off from the preprocessing chamber 702 by a gate not shown in the figure. In Embodiment 3 an evaporation chamber having the structure shown in Figs. 2A and 2B is used as the evaporation chamber (A) 703.

[0062]

A substrate 704 conveyed to the evaporation chamber (A) 703, and

an evaporation source 705 prepared in the evaporation chamber (A) 703, are moved in the direction of the arrows, respectively, and film formation is performed. Note that Figs. 2A and 2B may be referred to regarding detailed operation of the evaporation chamber (A) 703. A hole injecting layer is deposited in the evaporation chamber (A) 703 in Embodiment 3. A known material may be used as the hole injecting layer.

[0063]

Next, reference numeral 706 denotes an evaporation chamber for film formation of an organic EL material by evaporation, and is referred to as an evaporation chamber (B). The evaporation chamber (B) 706 is prepared with an evacuation system 700d. Further, it is hermetically sealed off from the evacuation chamber (A) 703 by a gate not shown in the figure. An evaporation chamber having the structure shown in Figs. 2A and 2B is formed as the evaporation chamber (B) 706 in Embodiment 3. The explanation of Figs. 2A and 2B may therefore be referred to regarding detailed operation of the evaporation chamber (B) 706. Further, a light emitting layer for emitting red color light is deposited in the evaporation chamber (B) 706. A known material may be used as the light emitting layer which emits red color light.

[0064]

Next, reference numeral 707 denotes an evaporation chamber for film formation of an organic EL material by evaporation, and is referred to as an evaporation chamber (C). The evaporation chamber (C) 707 is prepared with an evacuation system 700e. Further, it is hermetically sealed off from the evacuation chamber (B) 706 by a gate not shown in the figure. An evaporation chamber having the structure shown in Figs. 2A and 2B is formed as the evaporation chamber (C) 707 in Embodiment 3. The explanation of Figs. 2A and 2B may therefore be referred to regarding detailed operation

of the evaporation chamber (C) 707. Further, a light emitting layer for emitting green color light is deposited in the evaporation chamber (C) 707. A known material may be used as the light emitting layer which emits green color light.

[0065]

Next, reference numeral 708 denotes an evaporation chamber for film formation of an organic EL element by evaporation, and is referred to as an evaporation chamber (D). The evaporation chamber (D) 708 is prepared with an evacuation system 700f. Further, it is hermetically sealed off from the evacuation chamber (C) 707 by a gate not shown in the figure. An evaporation chamber having the structure shown in Figs. 2A and 2B is formed as the evaporation chamber (D) 708 in Embodiment 3. The explanation of Figs. 2A and 2B may therefore be referred to regarding detailed operation of the evaporation chamber (D) 708. Further, a light emitting layer for emitting blue color light is deposited in the evaporation chamber (D) 708. A known material may be used as the light emitting layer which emits blue color light.

[0066]

Next, reference numeral 709 denotes an evaporation chamber for film formation of a conducting film (a metallic film which becomes a cathode is used in Embodiment 3), which becomes an anode or a cathode of the EL element, by evaporation, and is referred to as an evaporation chamber (E). The evaporation chamber (E) 709 is prepared with an evacuation system 700g. Further, it is hermetically sealed off from the evacuation chamber (D) 708 by a gate not shown in the figure. An evaporation chamber having the structure shown in Figs. 2A and 2B is formed as the evaporation chamber (E) 709 in Embodiment 3. The explanation of Figs. 2A and 2B may therefore be referred to regarding detailed operation of the evaporation chamber (E)

709.

[0067]

An Al-Li alloy film (an alloy film of aluminum and lithium) is deposited in the evaporation chamber (E) 709 as the conducting film which becomes a cathode of the EL element. Note that it is also possible to co-evaporate an element belonging to group 1 or group 2 of the periodic table, and aluminum.

[0068]

Next, reference numeral 710 denotes a sealing chamber, and it is prepared with an evacuation system 700h. Further, it is hermetically sealed off from the evacuation chamber (E) 709 by a gate not shown in the figure. Embodiment 1 may be referred to regarding an explanation of the sealing chamber 710. Furthermore, an ultraviolet light irradiation mechanism (not shown in figure) is provided on the inside portion of the sealing chamber 710, similar to Embodiment 1.

[0069]

Finally, reference numeral 711 denotes an unload chamber, and it is prepared with an evacuation system 700i. The substrate on which the EL element is formed is removed from here.

[0070]

As described above, it thus becomes possible to manufacture an EL display device having high reliability by using the film formation apparatus shown in Fig. 7 because processing can be finished up through the point, without exposure to the atmosphere, at which the EL element is completely sealed into an airtight space. An EL display device can furthermore be manufactured at a high throughput in accordance with the in-line method.

[0071]

[Embodiment 4]

A case of using a film formation apparatus of the present invention in an in-line method is explained using Fig. 8. Reference numeral 801 denotes a load chamber in Fig. 8, and conveyance of a substrate is performed here. An evacuation system 800a is prepared in the load chamber 801, and the evacuation system 800a has a structure containing a first valve 81, a turbo-molecular pump 82, a second valve 83, and a rotary pump (oil-sealed rotary pump) 84.

[0072]

Next, reference numeral 802 denotes a preprocessing chamber for processing a surface of an anode or a cathode of an EL element (in Embodiment 4, an anode), and the preprocessing chamber 802 is prepared with an evacuation system 800b. Further, it is hermetically sealed off from the load chamber 801 by a gate not shown in the figure. The preprocessing chamber 802 can be changed variously depending upon the manufacturing process of the EL element, and in Embodiment 4 heat treatment of the surface of the anode made from the transparent conductive film can be performed at between 100 and 120°C in oxygen while irradiating ultraviolet light.

[0073]

Next, reference numeral 803 denotes an evaporation chamber for film deposition of an organic EL material by evaporation, and the evaporation chamber 803 is prepared with an evacuation system 800c. Further, it is hermetically sealed off from the preprocessing chamber 802 by a gate not shown in figure. In Embodiment 4 an evaporation chamber having the structure shown in Figs. 2A and 2B is used as the evaporation chamber 803. A substrate 804 conveyed to the evaporation chamber 803, and an evaporation source 805 prepared in the evaporation chamber 803, are moved in the direction of the arrows, respectively, and film formation is

performed.

[0074]

In Embodiment 4, it is preferable to switch the evaporation source 803 or the shadow mask (not shown) at the time of film deposition in the evaporation chamber 803 in order to form a conductive film to be hole injection layer, a red light emitting layer, a green light emitting layer, a blue light emitting layer or a cathode. In Embodiment 4, the evaporation chamber 803 is connected with a reserve chamber 806, in which the evaporation source and the shadow mask are stored to switch appropriately.

[0075]

Next, reference numeral 807 denotes a sealing chamber, and it is prepared with an evacuation system 800d. Further, it is hermetically sealed off from the evacuation chamber 803 by a gate not shown in the figure. Embodiment 1 may be referred to regarding an explanation of the sealing chamber 807. Furthermore, an ultraviolet light irradiation mechanism (not shown in the figure) is provided on the inside portion of the sealing chamber 807, similar to Embodiment 1.

[0076]

Finally, reference numeral 808 denotes an unload chamber, and it is prepared with an evacuation system 800e. The substrate on which the EL element is formed is removed from here.

[0077]

As described-above, it thus becomes possible to manufacture an EL display device having high reliability by using the film formation apparatus shown in Fig. 8 because processing can be finished up through to the point, at which the EL element is completely sealed into an airtight space without exposure to the atmosphere. An EL display device can furthermore be manufactured at a high throughput in accordance with the

in-line method.

[0078]

By using the film formation apparatus of the present invention, it becomes possible to perform film formation, at high throughput, of a thin film having high uniformity in its film thickness distribution inside of the substrate surface.

[Brief Description of the Drawings]

- [Fig. 1] Diagrams showing a structure of an evaporation source;
- [Fig. 2] Diagrams showing a structure of an evaporation chamber;
- [Fig. 3] A diagram showing a structure of an evaporation chamber;
- [Fig. 4] A diagram showing a structure of a film formation apparatus;
- [Fig. 5] A diagram showing a structure of a film formation apparatus;
- [Fig. 6] A diagram showing a structure of a film formation apparatus;
- [Fig. 7] A diagram showing a structure of a film formation apparatus;
- and
- [Fig. 8] A diagram showing a structure of a film formation apparatus.

[Name of Document] Abstract

[Summary]

[Problem] The present invention provides a film formation apparatus having high uniformity in its film thickness distribution.

[Solving Means] An evaporation source is used in which an evaporation cell, or a plurality of the evaporation cells, having a longitudinal direction is formed, and by moving the evaporation source in a direction perpendicular to the longitudinal direction of the evaporation source, a thin film is formed on a substrate. By making the evaporation source longer, the uniformity of the film thickness distribution in the longitudinal direction is increased. The evaporation source is moved, film formation is performed over the entire substrate, and therefore the uniformity of the film thickness distribution over the entire substrate can be increased.

[Selected Drawing] None



Filing Date : December 27, 1999

Reference Number = P004528-12

Application No. : 11-371349


[Name of Document] Drawing

RECEIVED

NOV 18 2002

TO 1500

[FIG. 1]







Reference Number = P004528-12

Filing Date : December 27, 1999

Application No. : 11-371349

RECEIVED

[FIG. 2]



(B)



Reference Number = P004528-12

Filing Date : December 27, 1999


Application No. 11-371349

RECEIVED


OCT 28 1999

0051 01

[FIG. 3]



[FIG. 4]





Reference Number = P004528-12

Filing Date : December 27, 1999


Application No. 11-371349

RECEIVED

NOV 8 8 1999

0071 07

[FIG. 5]





Reference Number = P004528-12


Filing Date : December 27, 1999


Application No, 11-371349

RECEIVED

OCT 8 1999
JC 1300

[FIG. 6]







Reference Number = P004528-12

Filing Date : December 27, 1999

Application No. 11-371349

[FIG. 8]

RECEIVED
NOV 18 1999
10 11 00

